

DUROSTICK D-5



Cementitious acrylic adhesive for decorative bricks and stones



PROPERTIES

Coarse, cementitious acrylic adhesive, reinforced with resins. Suitable for coat thicknesses of up to 15mm. It has strong adhesion, and high bonding strength. It is moisture resistant with zero vertical slip. The adhesive is specially modified, so that during the installation of the decorative bricks, its residues are used for the grouting of the lining. Classified C2T per EN 12004.(MIRTEC/Cert. No. 3357).

APPLICATIONS

DUROSTICK D-5 adhesive is suitable for linings with cement or ceramic bricks as well as with irregularly shaped stone slabs. Use it to install both interior decorative finishes and exterior building facade linings. The product is also suitable for the installation of stone slabs, cement tiles, and natural stone on both walls and floors. The addition of the acrylic emulsion D-20 or DUROSTOP of DUROSTICK, in the mixing water at a ratio of 1 part emulsion to 2 parts water or DUROMAX at a ratio of 1 part emulsion to

5 parts water increases the flexibility of the adhesive, ensuring excellent 'behavior' in intense expansions/contractions and natural or artificial vibrations.

USE

1. Surface preparation

The application surface must be clean, free of loose materials, dust and paints. Soak the surface well before application. Prime unsound surfaces using the micromolar stabilizer, AQUAFIX or the acrylic emulsion D-20 of DUROSTICK, diluted with water at a ratio of 1 part D-20 to 2 parts water.

2. Application

a) Installation: Empty 25kg of D-5 in a container with 5.5lt of clean, cool water. Stir with a low-rpm drill or use a clean cement mixer, until a lump free, homogeneous mass is created. Allow for the mixture to mature for 5-10 minutes. During use, stir periodically, without adding extra water. The mixture remains workable for 1.5-2 hours. Depending on the application, apply the adhesive using a gauging trowel or a notched trowel. The

DUROSTICK D-5



Cementitious acrylic adhesive for decorative bricks and stones

open time of the applied adhesive may be reduced to just a few minutes, when applied to very absorbent substrates.

b) Grouting: After the installation of decorative bricks or stones and within 8-10 minutes, smooth the grout joint from the residue of the adhesive by using the appropriate pointing tool or a thin rounded blade. Finish with a clean, damp soft sponge. Remove any residues with a clean, damp sponge, within 15 minutes of completion of the application.

NOTES

- If the aesthetic need and the design calls for other colors than gray, use the white mortar D-5 and color it with DUROCOLOR POWDER-C pigments in powder form, and create 96 permanent colors respectively.
- After hardening, the product is harm-less to health and the environment.

CLEANING

Clean all tools with water, immediately after use.

CONSUMPTION

5-10kg/m², depending on the surface smoothness, as well as the width and the depth of the joints.

STORAGE

Store in the factory sealed packages, in dry and shaded places for at least 12 months from production date.

SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product packaging or the Material Safety Data Sheet.

PACKAGING

Paper bag of 25kg on 1,500kg pallet

TECHNICAL SPECIFICATIONS (Measurement conditions 23°C and 50% R.H.)	
Form - Color	Cementitious mortar - White, gray
Shades	The white mortar can be colored in 48 colors by adding pigments in powder form, DUROCOLOR POWDER-C, yielding 96 distinct colors
Toxic	No
Bulk density of dry mortar	1.40±0.05kg/lt
Bulk density of fresh mortar	1.90±0.05kg/lt
Maximum grain size	1.0mm
Water requirement	5.5lt water in 25kg mortar
Application temperature	From +5°C to +35°C
Temperature resistance	From -35°C to +90°C
Application thickness	Up to 15mm
Vertical slip, per EN 1308	< 0.5mm
Pot life	Up to 2 hours
Open adhesion time, per EN 1346	20 minutes
Time for minor adjustments	10 minutes
PRODUCT PERFORMANCES	
Adhesive strength per EN 1348 after:	
• 28 days	1.70 N/mm ²
• Thermal ageing at +70°C	1.20 N/mm ²
• Water immersion for 21 days	1.30 N/mm ²
• 25 freeze - thaw cycles	1.40 N/mm ²
<i>The experimental measurements were performed per EN 12004, in the Chemical Laboratory of DUROSTICK and were confirmed by the measurements of initial type from MIRTEC (Cert. No: 3357). •NOTE: The product exceeds on average the statutory requirements for C2 adhesive.</i>	

DUROSTICK D-5



Cementitious acrylic adhesive for decorative bricks and stones

DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS & MORTARS

ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel:

+30 211 60 03 500-599, +30 210 55 16 500, +30 210 55

98 350, Fax: +30 210 55 99 612

THESSALONIK: INDUSTRIAL PARK-SINDOS, S.B. 44,

STREET, DA 0, GR: 570 22, Tel: +30 2310 795 797, +30

2310 797 365, Fax: +30 2310 797 367

E-mail: info@durostick.com