

VELATURA



Solvent-based undercoat for enamel paints



■ PROPERTIES

White alkyd-based undercoat for enamel paints, suitable for the preparation of wood surfaces and walls. It adheres strongly, has high coverage (also fills), works, spreads and sands with ease. Creates an ideal, smooth surface and yields extra durability to the topcoat.

■ APPLICATIONS

DUROSTICK VELATURA applies on new or existing spackled wood surfaces (doors, windows). It also applies on skimmed surfaces made of marble-based plaster and gypsum boards.

■ USE

1. Surface preparation

All surfaces to be primed, have to be sanded with the appropriate sandpaper. They also have to be dry, dust free, and completely clean, without any dust, oils and salts.

New wood surfaces

Remove as many knots as required and ensure protection from antifungal and wood-boring insects

using the clear preservative DUROXYL Wood Protection / Conditioner of DUROSTICK.

Once dry, spackle with STUCOFIX putty and sand the surfaces with the appropriate sandpaper to smooth them.

On sanded and cleaned surfaces, apply 1-2 coats of VELATURA. Once dry, sand as needed to create the perfect undercoat for 2 coats of DUROLUX, the enamel top coat of DUROSTICK.

Existing wood surfaces

Thoroughly remove all loose paint and spackle any imperfections with STUCOFIX putty. Continue by following the same procedure as described in the section 'New wood surfaces' (from the spackled step onwards).

Gypsum board surfaces

Skim using STUCOFIX-P, STUCOFIX putty or DUROSTICK D-67.

Once dry, sand the surface, remove all the dust, and apply VELATURA of DUROSTICK.

Wall surfaces from marble-based plaster

Skim coat using STUCOFIX-P, STUCOFIX putty, POWDER COAT or GRANULAR of DUROSTICK. Once dry, apply VELATURA of DUROSTICK.

VELATURA



Solvent-based undercoat for enamel paints

Complete by painting with emulsion, acrylic or enamel paints of DUROSTICK. This will create a perfect result presenting high strength.

2. Application

Mix well before any use. Apply VELATURA using a roller, a brush or an airless sprayer. Dilute by 5-10% using THINNER 101 of DUROSTICK or white spirit. Once dry, sand with the appropriate sandpaper to create a smooth surface to which the finish paint is applied.

■ CLEANING

Clean all tools with THINNER 101 of DUROSTICK or white spirit immediately after use.

■ COVERAGE

Approximately 10-12m²/lt per coat, depending on the texture, the absorbency of the surface and the application method.

■ STORAGE

Store in shaded places away from any heat source, for 24 months from production date.

■ SAFETY DIRECTIONS

The product is classified as harmful.

However, it is recommended to keep away from the reach of children and apply it in well ventilated areas. Before use, refer to the cautions on the product packaging or the Safety Data Sheet.

■ PACKAGING

Carton box with 12pcs of 750ml each one

Carton box with 4pcs of 2.5lt each one

TECHNICAL SPECIFICATIONS

■ Form - Color	Thixotropic liquid - White
■ Density	1.50±0.05kg/l
■ Application temperature	From +10°C to +35°C
■ Dilution	Up to 5-10% with THINNER 101 or white spirit
■ Application method	Brush, roller or spray gun
■ Drying time	3-4 hours (touch dry), at +20°C
■ Recoating time	After 16-18 hours, at +20°C

V.O.C. (Volatile Organic Compounds):

Limit value of maximum V.O.C. content per EU (Directive 2004/42/CE) for the particular product (Class A/g: 'Primers' Type SB): 350gr/lt (2010). The ready to use product contains maximum 340gr/lt V.O.C.