

DUROSTICK D-26



Corrosive and remover for paints & varnishes



PROPERTIES

The paint and varnish corrosive, D-26 of DUROSTICK is a specific purpose rich mixture of special corrosive solvents. Those solvents are specially modified (contains no dichloromethane) to effectively ensure the removal of all kinds of existing paints. Distinguished for its immediate action, it removes enamel paints and solvent or water based varnishes as well as lacquer and polyurethane paints. It removes with ease epoxy based paints, nitrocellulose and bake paints as well as electrostatic paints, emulsion and acrylic paints etc. Available in gel form, for controlled application and flow.

APPLICATIONS

D-26 removes existing or new paints from metal, wood and building surfaces. A single application removes paints and varnishes with exceptional ease.

USE

1. Surface preparation

Remove any loose sections from the applicable surfaces (if existing).

2. Application

Protect your hands by using gloves. Use a brush to apply a thick coat on the surfaces. Allow the product to act for 3-10 minutes, depending on the thickness and composition of the material to be removed. Use a putty knife or a triangle scraper to remove the deteriorated paints. If some residue remains, just repeat the process. Once dry, sand, prime the surface (where necessary) and finally paint.

CONSUMPTION

1lt/2-4m², depending on the nature and the layers of the covering coating(s) to be removed.

STORAGE

Store in the factory sealed container, at temperatures between 5°C and 35°C, and away from

DUROSTICK D-26



Corrosive and remover for paints & varnishes

any heat source, for up to 12 months from production date.

SAFETY DIRECTIONS

The product is classified as highly flammable. It is recommended to keep locked away from the reach of children and apply it in well ventilated areas. Before use, refer to the cautions on the product packaging or the Material Safety Data Sheet.

PACKAGING

Carton box with 20 pcs of 250ml each one
 Carton box with 12 pcs of 500ml each one
 Carton box with 12pcs of 1lt each one

TECHNICAL SPECIFICATIONS	
Form - Color	Thick gel - Transparent
Density	1.00±0.05kg/lt
Application temperature	From +5°C to +35°C
Reactivity	3-10 minutes, depending on the thickness and the composition of paint
Dilution	The product is ready for use. Do not dilute.

DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS & MORTARS

ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel:

+30 211 60 03 500-599, +30 210 55 16 500, +30 210 55

98 350, Fax: +30 210 55 99 612

THESSALONIK: INDUSTRIAL PARK-SINDOS, S.B. 44,

STREET, DA 0, GR: 570 22, Tel: +30 2310 795 797, +30

2310 797 365, Fax: +30 2310 797 367

E-mail: info@durostick.com

The technical specifications and directions of use contained in this technical brochure are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.