

EXTRA POWER



100% Vinyl acrylic deformable tile adhesive



PROPERTIES

High performance, white cementitious adhesive, fortified with vinyl acrylic resins. Distinct for its high thixotropy, flexibility and its zero vertical slip. Resistant to permanent moisture and frost. After its final cure, the product is resistant to mold growth. Allows for coatings of up to 20mm, without 'sagging', while it has an extended open time.

Classified C2TE S2 per EN 12004 and EN 12002 (MIRTEC/Cert. No. 3355).

APPLICATIONS

EXTRA POWER is ideal for bonding larger size, low and non absorbent tiles and granite, on external building facades. It is necessary for adhering very hard and resilient tiles, like klinker, gres, porcellanato, porcellanato smaltato and ceramic or glass mosaics. Distinguished for its resistance to expansions and contractions indoors, related to radiant heating, as well as outdoor spaces, with strong temperature variations, like balconies, patios and terraces. Its durability and resilience makes it stand out for installations in areas

with permanent moisture, such as swimming pools, fountains, bathrooms, showers, etc.

It is suitable for heavy traffic areas such as car showrooms, airport terminals, shopping malls, super markets, as well as dining rooms and public areas. It is ideal for every kind of stable substrate, such as cement screeds, brushable cementitious substrates, prefabricated concrete walls, existing tiles, terrazzo and mosaic, as well as marble, aircrete or gypsum and marble based top coats. Its high thixotropy allows for wall tile installations top down.

USE

Surface preparation:

The application surface has to be sound, clean, free of loose materials, dust, paint, grease and oils. The surface has to be soaked before the application. It is necessary to prime all absorbent substrates and aircrete, using DUROSTICK ACRYLIC EMULSION or D-20, at a mixing ratio of 1:1 with water. It is necessary to prime all gypsum boards using the DUROSTICK micromolar

EXTRA POWER



100% Vinyl acrylic deformable tile adhesive

stabilizer, AQUAFIX or SOLVENT BASED PRIMER. Lightweight or else, unstable cement screeds, must necessarily be primed with DUROSTICK ACRYLIC EMULSION or D-20 at a ratio of 1part additive to 2 parts water or 1 part DUROMAX to 5 parts water. Follow all balcony and terrace, bathroom, shower and swimming pool applications by coating the substrate with HYDROSTOP FLOOR, with 2-3 successive, cross-wise coats to ensure the waterproofing of the substrate.

Application:

Empty the adhesive into a clean container with cool water at a ratio of 2 parts water to 5 parts mortar (7.0-7.5lt water to 25kg mortar) and mix with a low rpm electric mixer until a lump free, homogeneous mass is created. Allow the mixture to mature for 5-10 minutes. During use mix periodically, without adding extra water. Apply the adhesive using a notched trowel and spread on the substrate. Then, coat as much surface as is required to work for the next 15-30 minutes (depending on weather conditions), thus avoiding skin formation. Finally, install the tiles in the selected position by tapping softly with a rubber mallet. The application of the adhesive in the case of medium and large format tiles, is done by the method of double coating (on the substrate, but also on the tile).

HELPFUL TIP

Installing tiles on high stress areas (balconies, terraces, swimming pools, garages) requires the use of high quality adhesives. This is because, besides the project assurance high quality adhesives provide, their cost is comparatively very small to the purchase value of the tiles as well as their installation cost by qualified professionals.

NOTE

On exterior surfaces, it is highly recommended to create expansion joints every 16-20m². Prime the expansion joints with PRIMER-PU, to improve grip, fill them with the backer rod of DUROSTICK, DS-265, and seal them with the polyurethane sealant, DUROFLEX-PU. Similarly, seal all the joints (5-8mm) at the junction of the tiles and vertical surfaces throughout the perimeter. Alternatively the application of DS POLYMER sealant, available in 32 colors (same ones

with the grout colors of DUROSTICK), ensures sealing without cracking at the junction of the tiles with the skirting and above it as well. On floors with radiant heating systems, it is recommended to create expansion joints every 20m² and fill them with DS POLYMER sealant, available in 32 colors..

CONSUMPTION

3-5kg/m², depending on the size of the notch of the trowel, the smoothness of the substrate and the dimensions of the tiles.

CLEANING

Clean all tools with water, immediately after use.

STORAGE

Store in the factory sealed packages, in dry and shaded places, for at least 12 months from production date.

SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product's package or the Material Safety Data Sheet.

PACKAGING

Paper bag of 25kg on 1,500kg pallet

EXTRA POWER



100% Vinyl acrylic deformable tile adhesive

TECHNICAL SPECIFICATIONS (Measurement conditions 23°C and 50% R.H.)	
Form - Color	Cementitious mortar - White
Toxic	No
Bulk density of dry mortar	1.30±0.05kg/lt
Slip per EN 1308	<0.2mm
Water requirement:	7,0lt water per 25kg mortar
Application temperature	From +5°C to +35°C
Temperature resistance	From -35°C to +90°C
Pot life	7 hours
Application thickness	Up to 20mm
Open time per EN 1346	30 minutes
Time for minor adjustments:	35 minutes
Grouting	After 4-8 hours on wall, after 24 hours on floor
Foot traffic	After 24 hours
Delivery to use	After 12-14 days
PRODUCT PERFORMANCES	
Adhesion strength, per EN 1348, after:	
• 28 days	≥2.30 N/mm
• Thermal ageing at +70°C	≥1.90 N/mm ²
• Water immersion for 21 days	≥1.70 N/mm ²
• 25 freeze - thaw cycles	≥1.55 N/mm ²
• Deformability S per EN 12002	S≥5mm.
The experimental measurements were performed per EN 12004, in the Chemical Laboratory of DU-ROSTICK and were confirmed by the measurements of initial type from MIRTEC (Cert. no: 3355). NOTE: The product exceeds on average the statutory requirements for C2 adhesive.	

CE

DUROSTICK S.A.
 ASPROPYRGOS ATHENS PC:193 00
GREECE
07

DoP No.: 009
EN 12004:2007+ A1:2012

EXTRA POWER
 Improved highly deformable cementitious adhesive
 with reduced slip and extended open time
 Interior - exterior use

- Reaction to fire:	Euroclass A1
- Release of dangerous substances:	see MSDS

Bond Strength as:
 - Tensile adhesion strength: 1.00 N/mm²
 Durability for:
 - Tensile adhesion strength after heat ageing: 1.00 N/mm²
 - Tensile adhesion strength after water Immersion: 1.00 N/mm²
 - Tensile adhesion strength after freeze-thaw cycles: 1.00 N/mm²

DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS & MORTARS

ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel:

+30 211 60 03 500-599, +30 210 55 16 500, +30 210 55

98 350, Fax: +30 210 55 99 612

THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,

STREET, DA 10, GR: 570 22, Tel: +30 2310 795 797, +30

2310 797 365, Fax: +30 2310 797 367

E-mail: info@durostick.com

The technical specifications and directions of use contained in this technical brochure are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.