

EXTRA POWER GEL



Flexible, thixotropic adhesive for tiles and natural stones



PROPERTIES

Cementitious, fine-grained tile adhesive, with high performance. The inorganic, amorphous silicates and the new technology resins contained in its composition, provide the mixture unique GEL properties, excellent thixotropy, workability and ease of application.

Classified C2TE S1 per EN 12004 and EN 12002.

ADVANTAGES

- Wide variation in the process water rate from 28% to 34% without affecting the workability and the final performance of the adhesive.
- Fine-grained, suitable for adhesives with a small thickness of glue.
- Volume stability. It can be applied in thicknesses from 2mm up to 20mm, but also used for repairs and smoothing of the substrate before tiles installation.
- Zero shrinkage.
- Offers the possibility of adhering large size tiles.
- Zero vertical slip.
- Strong adhesion and zero slip.

- Extremely extended open time for adhering and minor corrections.
- Particularly resistant to the cooling-thawing effect.
- Extremely resistant to moisture, frost, contractions and expansions and natural and mechanical stresses.

APPLICATIONS

EXTRA POWER GEL is suitable for all types of tiles, from mosaic to very large tiles, but also natural stones. It is applied indoors and outdoors, on solid substrates, such as:

- Waterproofed surfaces with either elastomeric waterproofers or brushable cementitious
- Concrete, plaster or prefabricated concrete wall surfaces
- Verandas, terraces
- Spaces with permanent moisture, such as fountains, bathrooms, showers etc.
- Mosaics or tile refurbishments in heavy traffic areas

EXTRA POWER GEL



Flexible, thixotropic adhesive for tiles and natural stones

EXTRA POWER GEL ensures the installation for all types of tiles and stones with minimal absorption, such as:

- Tiles of all sizes
- Glass mosaic, klinker, glazed gres
- Cotto, honed marble, artificial stones
- Any type of granite tiles, absorbent or else
- Cork and expanded polyurethane boards
- Every type of marble, even green marble.

USE

1. Surface preparation

The application surface has to be sound, clean, free of loose materials, dust, paint, grease and oils. The surface has to be soaked before the application. It is necessary to prime all absorbent substrates and aircrete, using DUROSTICK ACRYLIC EMULSION or D-20, at a mixing ratio of 1:1 with water. It is necessary to prime all gypsum board and plaster surfaces, using the DUROSTICK micromolar stabilizer, AQUAFIX or SOLVENT BASED PRIMER. Lightweight or else, unstable cement screeds, must necessarily be primed with DUROSTICK ACRYLIC EMULSION or D-20 at a ratio of 1-part additive to 2-parts water or 1-part DUROMAX to 5 parts water.

Smooth or non-absorbent surfaces, primed with quartz primer DS-290 of DUROSTICK.

For balcony, terrace, bathroom and shower the application of HYDROSTOP FLOOR or D-1 FLEX will follow, at 2-3 successive, crosswise layers to ensure the waterproofing of the substrate.

2. Application

Empty the product into a clean container with cool water at a ratio of 25kg mortar to 7.0lt water for a thixotropic adhesive or 25kg mortar to 8.0lt water for liquid adhesive. Stir with a low rpm drill until a lump free, homogeneous mass is created. Allow the mixture to mature for 5-10 minutes and mix periodically, without adding extra water. Apply the adhesive using a notched trowel, and spread on the substrate. Then, coat as much surface as is required to work for the next 15-30 minutes (depending on weather conditions), thus avoiding skin formation. Finally, install the tiles or other materials to be installed, in the selected position by tapping softly with a rubber mallet. The

application of the adhesive in the case of large tiles is done by the method of double coating (on the substrate, but also on the tile).

NOTES

On exterior surfaces, it is highly recommended to create expansion joints every 16-20m². Prime the expansion joints with PRIMER-PU, to improve grip, fill them with the backer rod of DUROSTICK, DS-265, and seal them with the polyurethane sealant, DUROFLEX-PU. Following the same way, seal all the joints (5-8mm) at the junction of the tiles and vertical surfaces throughout the perimeter.

Alternatively, the application of DS POLYMER sealant, available in 32 colors (same ones with the grout colors of DUROSTICK), ensures sealing without cracking at the junction of the tiles with the skirting and above it as well. On floors with radiant heating systems, it is recommended to create expansion joints every 20m² and fill them with DS POLYMER sealant, available in 32 colors.

CLEANING

Clean all tools with water, immediately after use.

CONSUMPTION

3-5kg/m², depending on the size of the notch of the trowel, the smoothness of the surface and the dimensions of the tiles.

STORAGE

Store in the factory sealed package, in dry and shady places, for at least 12 months from the date of production.

SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product's package or the Material Safety Data Sheet.

PACKAGING

25kg Paper bag on a 1.200kg pallet

EXTRA POWER GEL



Flexible, thixotropic adhesive for tiles and natural stones

TECHNICAL SPECIFICATIONS (Measurement conditions 23°C and 50% R.H.)

Form - Color	Cementitious mortar - White
Toxic	No
Bulk density of dry mortar	1.30±0.05kg/lt
Vertical slip per EN 1308	< 0.1mm
Water requirement for:	
Thixotropic adhesive	7.0lt water in 25kg mortar
Liquid adhesive	8.0lt water in 25kg mortar
Application temperature	From +5°C up to +35°C
Temperature resistance	From -30°C up to +90°C
Application thickness	Up to 20mm
Pot life	At least 7 hours
Open time per EN 1346	At least 30 minutes
Time for minor adjustments	25 minutes
Grouting	After 4-8 hours on wall, after 24 hours on floor
Foot traffic	After 24 hours
Delivery to use:	
Light traffic	1-3 days
Heavy traffic	2-5 days

PRODUCT PERFORMANCES

Adhesive strength per EN 1348 after:	
• 28 days	≥ 2.00 N/mm ²
• thermal ageing at +70°C	≥ 1.60 N/mm ²
• water immersion for 21 days	≥ 1.55 N/mm ²
• 25 freeze - thaw cycles	≥ 1.60 N/mm ²
Deformability S per EN 12002	2.5mm ≤ S < 5mm

NOTE: The product exceeds on average the statutory requirements for C2 adhesive.



DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS & MORTARS

ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel: +30 211 60 03 500-599, +30 210 55 16 500, +30 210 55 98 350, Fax: +30 210 55 99 612

THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44, STREET, DA 10, GR: 570 22, Tel: +30 2310 795 797, +30 2310 797 365, Fax: +30 2310 797 367

Email: info@durostick.com