


PROFESSIONAL



Resinous tile adhesive



PROPERTIES

Cementitious, high performance white adhesive for ceramic tiles, fortified with acrylic resins, and minimal vertical slip. Distinguished for its high initial and final bonding strengths, as it offers strong adhesion and extended open time. After its final curing, it is resistant to moisture and frost. Classified C2E per EN 12004. (MIRTEC/Cert. No. 3353).

APPLICATIONS

PROFESSIONAL is suitable for small and large size tile installations on floor cement screeds and plastered walls, both indoors and out. Adding DUROSTICK ACRYLIC EMULSION in the mixing water, at a ratio of 1:1, further enhances its characteristics so as to meet the requirements of S1 class (deformable adhesive) per EN 12002. The improved (as per its flexibility) adhesive, is suitable for non absorbent substrates, subjected to intense expansions and contractions, as well as for outdoor spaces that are exposed to adverse weather conditions. The adhesive is suitable for every type and size tile.

USE

Surface preparation:

The application surface has to be sound, clean, free of loose materials, dust, paint, grease and oils. The surface has to be soaked before the application. It is necessary to prime all absorbent substrates and aircrete, using DUROSTICK ACRYLIC EMULSION or D-20, at a mixing ratio of 1:1 with water. It is necessary to prime all dry-wall using the DUROSTICK micromolar stabilizer, AQUAFIX or SOLVENT BASED PRIMER. Lightweight or else, unstable cement screeds, must necessarily be primed with DUROSTICK ACRYLIC EMULSION or D-20 at a ratio of 1part additive to 2 parts water or 1 part DUROMAX to 5 parts water. Follow all balcony and terrace applications by coating the substrate with HYDROSTOP FLOOR, at 2-3 successive, cross-wise layers to ensure the waterproofing of the substrate.

Application:

Empty the adhesive into a clean container with cool water at a ratio of 2 parts water to 5 parts

PROFESSIONAL



Resinous tile adhesive

mortar (6.5-7.0lt water to 25kg mortar) and mix with a low rpm electric mixer until a lump free, homogeneous mass is created. Allow the mixture to mature for 5-10 minutes. During use mix periodically, without adding extra water. Apply the adhesive using a notched trowel, and spread on the substrate. Then, coat as much surface as is required to work for the next 15-30 minutes (depending on weather conditions), thus avoiding skin formation. Finally, install the tiles in the selected position by tapping softly with a rubber mallet.

NOTE

On outdoor surfaces, it is highly recommended to create expansion joints every 16-20m². Prime the expansion joints with PRIMER-PU, to improve grip, and seal them with the polyurethane sealant, DUROFLEX-PU. Similarly, seal all the joints (5-8mm) at the junction of the tiles and vertical surfaces throughout the perimeter. Alternatively the application of DS-POLYMER, in 32 colors (same with the grout colors of DUROSTICK), ensures sealing without cracking at the junction of the tiles with the skirting and above it as well.

CONSUMPTION

3-5kg/m², depending on the size of the notch of the trowel, the smoothness of the substrate and the dimensions of the tiles.

CLEANING

Clean all tools with water, immediately after use.

STORAGE

Store in factory sealed packages, in dry and shaded places for a minimum of 12 months after production date.

SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product's package or the Material Safety Data Sheet.

PACKAGING

Paper bag of 25kg on 1,500kg pallet

| TECHNICAL SPECIFICATIONS (Measurement conditions 23°C and 50% R.H.) | |
|--|--|
| Form - Color | Cementitious mortar – White |
| Toxic | No |
| Bulk density of dry mortar | 1.35±0.05kg/lt |
| Water requirement: | 6.5lt water per 25kg mortar |
| Application temperature | From +5°C to +35°C |
| Temperature resistance | From -35°C to +90°C |
| Pot life | 5 hours |
| Application thickness | Up to 10mm |
| Open time per EN 1346 | 30 minutes |
| Time for minor adjustments: | 25 minutes |
| Grouting | After 3-6 hours on wall, after 24 hours on floor |
| Foot traffic | After 24 hours |
| Delivery to use | After 10-14 days |
| PRODUCT PERFORMANCES | |
| Adhesion strength, per EN 1348, after: | |
| • 28 days | 1.30 N/mm ² |
| • Thermal ageing at +70°C | 1.15 N/mm ² |
| • Water immersion for 21 days | 1.20 N/mm ² |
| • 25 freeze - thaw cycles | 1.20 N/mm ² |
| The experimental measurements were performed per EN 12004, in the Chemical Laboratory of DUROSTICK and were confirmed by the measurements of initial type from MIRTEC (Cert. No. 3352). NOTE: The product exceeds the statutory requirements for C2 adhesive. | |

PROFESSIONAL



Resinous tile adhesive



DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS & MORTARS
ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel:
+30 211 60 03 500-599, +30 210 55 16 500, +30 210 55
98 350, Fax: +30 210 55 99 612
THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,
STREET, DA 10, GR: 570 22, Tel: +30 2310 795 797, +30
2310 797 365, Fax: +30 2310 797 367
E-mail: info@durostick.com