


D-23



Marble & granite adhesive



■ PROPERTIES

White adhesive reinforced with resins, for marble and granite installations. Distinguished for its extremely strong adhesion, initial and final adhesive strength. After its complete cure, it is moisture and frost resistant. It does not stain white and light color marbles.

Classified C2T per EN 12004.

The product has received an Environmental Product Declaration (EPD) following an assessment of the environmental impact of its life cycle.

Registration number: S-P-13561,
The International EPD® System.

■ APPLICATIONS

DUROSTICK D-23 is suitable for marble and granite linings on walls, floors, stairs, both indoors and out. It is suitable and necessary for installing textured marble and stone on building facades. Provides excellent adhesion to regular and irregular shaped

floor slabs, subject to increased mechanical stresses. Adding DUROSTICK ACRYLIC EMULSION in the mixing water, at a ratio of 1:1, or 1 part DUROMAX to 5 parts water, further improves its characteristics.

With this improvement, the adhesive is perfectly appropriate for marble installations on building facades, up to 3m high and from 1-3cm thick (slab thickness), avoiding mechanical support/clips (check with your local and National building codes). The enhanced, flexible adhesive is suitable for installing marble and slabs on outdoor substrates and over surfaces with radiant heating systems subjected to intense expansions and contractions.

■ USE

1. Surface preparation

The application surface must be sound, clean, free of loose materials, dust, paint, grease, oils and it should be soaked before the application. All unstable and absorbent substrates must be primed, using the

The technical specifications and directions of use contained in this technical data sheet are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.

D-23



Marble & granite adhesive

micromolar stabilizer, AQUAFIX. Alternatively, use the acrylic emulsion, D-20 of DUROSTICK diluted in clean water, at a mixing ratio of 1 part emulsion to 2 parts water, thus achieving an unbreakable bonding. Follow all balcony and terrace applications by coating the substrate with HYDROSTOP FLOOR or D1, with 2-3 successive, crosswise coats to ensure the waterproofing of the substrate.

2. Application

Empty the adhesive into a clean container with cool water at a ratio of 2 parts water to 5 parts mortar (7.0-7.5lt water to 25kg mortar) and mix with a low-rpm drill until a lump free, homogeneous mass is created. Allow the mixture to mature for 5-10 minutes. During use mix periodically, without adding extra water. Apply the adhesive using a gauging trowel, 'comb' with a notched trowel and spread on the substrate. Then, coat as much surface as is required to work for the next 10-20 minutes (depending on weather conditions), thus avoiding skin formation. Finally, install the marble in the selected position by tapping softly with a rubber mallet.

■ CLEANING

Clean all tools with water, immediately after use.

■ CONSUMPTION

4-7kg/m², depending on the size of the notch of the trowel, the smoothness of the substrate and the dimensions of the marble and stone slabs.

■ STORAGE

Store in the factory sealed packages, in dry and shaded places, for 12 months from production date.

■ SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product packaging or the Safety Data Sheet.

■ PACKAGING

Paper bag of 25kg on 1,500kg pallet.

TECHNICAL SPECIFICATIONS

(Measurement conditions 23°C and 50% R.H.)

■ Form – Color	Cementitious mortar - White
■ Bulk density of dry mortar	1.40±0.05kg/lt
■ Maximum grain size	1.3mm
■ Slip per EN 1308	<0.5mm
■ Water requirement	7.0lt water in 25kg mortar
■ Application temperature	From +5°C to +35°C
■ Temperature resistance	From -35°C to +90°C
■ Application thickness	Up to 10mm
■ Pot Life	Approximately 3 Hours*
■ Open time per EN 1346	20 minutes*
■ Time for minor adjustments	25 minutes*
■ Foot traffic	After 24 hours
■ Delivery to use	After 10 days

PRODUCT PERFORMANCES

■ Adhesion strength, per EN 1348, after:	
• 28 days	2.20N/mm ²
• Thermal ageing at +70°C	1.70N/mm ²
• Water immersion for 21 days	1.80N/mm ²
• 25 freeze-thaw cycles	1.75N/mm ²

* Depending on the weather conditions (temperature, humidity).

NOTE: The product exceeds the statutory requirements for C2 adhesive.

DUROSTICK S.A.,
 MANUFACTURING OF ADHESIVES,
 PAINTS & MORTARS
ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00,
 Tel: +30 211 60 03 500-599, +30 210 55 16 500,
 +30 210 55 98 350, Fax: +30 210 55 99 612
THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,
 STREET, DA 10, GR: 570 22,
 Tel: +30 2310 795 797, +30 2310 797 365,
 Fax: +30 2310 797 367
 Email: info@durostick.com

The technical specifications and directions of use contained in this technical data sheet are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.