

D-11 SUPER FAST



Fast setting cementitious repair mortar



■ PROPERTIES

Fast setting and high early strength repair mortar, for interior and exterior use. The addition of water produces a mixture which is workable for 7 minutes, while the hardening process begins within 15 minutes. The strength developed in one hour is equivalent to that of a regular cement mortar after 24 hours of curing time.

Classified as concrete repair product, in PCC R2 category, per EN 1504-3.

■ ADVANTAGES

- Develops early mechanical strength.
- Exceptional adhesion to the substrate and excellent workability.
- Minimal shrinkage, without cracking.
- Resistant to frost, moisture, carbonation, and corrosion by chemicals, such as nitrates, sulfates, and chlorides.
- Does not contain chlorides or corrosive ingredients.
- Ideal for applications where quick project delivery is essential.

■ APPLICATIONS

D-11 SUPER FAST is recommended for safe and quick bonding when performing electrical and plumbing installations. Suitable for installing electrical panels and junction boxes, having comparative compression strength 40 times greater than traditional plaster, and without the potential risk of deterioration from moisture and rain.

It is necessary for all utility wells and manholes. It is suitable for anchoring machinery and equipment, and also for the installation of metal railings and wrought iron balusters on concrete walls. Use it also to bond the fiberglass mesh for plasters/renders on interior and exterior surfaces. It is highly effective for sealing holes in concrete walls, floors and ceilings and for installing corner beads.

■ USE

1. Surface preparation

The substrate must be clean, free from loose sections, dust and oils. It should be soaked thoroughly before application to ensure high adhesion.

D-11 SUPER FAST



Fast setting cementitious repair mortar

2. Application

Empty D-11 SUPER FAST into a clean container with water, at a mixing ratio of 3kg mortar to 0.7-0.8lt water, depending on the application. Mix thoroughly, until a lump free, homogeneous mass is created. Each coat can be applied to a thickness of up to 3cm.

■ NOTE

Apply a coat of corrosion inhibitor, RUST FREE POWDER of DUROSTICK to any metal surface that will be coated with D-11 SUPER FAST.

■ CONSUMPTION

Depending on the application.
Approximately 1.8kg of D-11 SUPER FAST to make 1lt of cured mix.

■ STORAGE

Store in the factory sealed packages, in dry and shaded places, protected from moisture and frost, for 10 months from production date.

■ SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product packaging or the Safety Data Sheet.

■ ATTENTION

Do not mix the product with additional water once it starts to set, because it will lose its mechanical strength.

■ PACKAGING

Carton box with 8 pcs of 3kg each one on 504kg pallet

DUROSTICK S.A.,
MANUFACTURING OF ADHESIVES,
PAINTS & MORTARS
ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00,
Tel: +30 211 60 03 500-599, +30 210 55 16 500,
+30 210 55 98 350, Fax: +30 210 55 99 612
THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,
STREET, DA 10, GR: 570 22,
Tel: +30 2310 795 797, +30 2310 797 365,
Fax: +30 2310 797 367
Email: info@durostick.com

TECHNICAL SPECIFICATIONS

(Measurement conditions 20°C and 50% R.H.)

■ Form - Color	Cementitious mortar – Gray
■ Bulk density of dry mortar	1.42±0.05kg/lt
■ Bulk density of fresh mortar	2.00±0.05kg/lt
■ Maximum grain size	0.7mm
■ Water requirement	0.7lt water in 3kg mortar
■ Application temperature	From +5°C to +30°C
■ Temperature resistance	From -30°C to +200°C
■ Pot life	7 minutes
■ Shrinkage per ASTM C596	Negligible
■ Resistance to continuous exposure to water	Excellent
■ Chloride ion content, per EN 1015-17	≤ 0.05%

PRODUCT PERFORMANCES

■ Resistance to flexion, per EN 12190, to:	
•28 days	≥ 5.00 N/mm ²
■ Compression resistance, per EN 12190, to:	
•24 hours	≥ 6.50 N/mm ²
•7 days	≥ 14.00 N/mm ²
•28 days	≥ 22.00 N/mm ²
■ Adhesion to concrete per EN 1542	≥ 1.20 N/mm ²
■ Thermal compatibility expressed as adhesion to concrete, per EN 13687, after:	
•50 freeze-thaw cycles	≥ 1.00 N/mm ²
•30 storm cycles	
•30 dry heat cycles	
■ Capillary water absorption, per EN 13057	w ≤ 0.45kg.m ⁻² .h ^{-0.5}
■ Reaction to fire	Class A1

Where 1 N/mm²=1MPa

The technical specifications and directions of use contained in this technical data sheet are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.