

VELATURA AQUA



Undercoat for enamel paints



■ PROPERTIES

Exceptional undercoat of water dispersion and acrylic-based, suitable for any water soluble enamel paint. It spreads evenly and it exhibits excellent adhesion to new surfaces and surfaces already painted with solvent-based enamel paints.

It works and sands easily, it dries quickly and has great coverage. It perfectly prepares each surface to accept finishing paint coats.

It is odorless, and ideal for indoor applications, especially in enclosed spaces with insufficient ventilation.

■ APPLICATIONS

VELATURA AQUA of DUROSTICK, easily applies on new and existing spackled wood surfaces (doors, windows etc.).

Apply it also on skimmed surfaces made of marble-based plaster and gypsum boards. It is highly recommended for children's rooms, hospitals, schools etc. Suitable for interior and exterior use.

■ USE

1. Surface preparation

Surfaces to be coated have to be sanded with the appropriate sandpaper. Also surfaces have to be dry, clean, free of dust, oils and salts.

New wood surfaces

Remove as many knots as required and ensure antifungal and wood-boring insect protection using the clear preservative DUROXYL Aqua TOTAL WOOD PROTECTION of DUROSTICK. Once dry, spackle with STUCOFIX putty and sand the surfaces with the appropriate sandpaper to smooth them.

On sanded and cleaned surfaces, apply 1-2 coats of the acrylic VELATURA AQUA.

Once dry, sand as needed and complete the application with 2 coats of the enamel paint DUROLUX AQUA of DUROSTICK.

Existing wood surfaces

Carefully remove any loose paints and spackle any imperfections with STUCOFIX putty. Continue by

VELATURA AQUA



Undercoat for enamel paints

following the same procedure as described in the section 'New wood surfaces' (from the spackled onwards).

Gypsum board surfaces

Spackle the surfaces with STUCOFIX-P, STUCOFIX putty or DUROSTICK D-67. Continue by applying a coat of acrylic VELATOURA AQUA of DUROSTICK.

Wall surfaces made of marble-based plaster

Spackle and skim using STUCOFIX putty, STUCOFIX-P or POWDER COAT of DUROSTICK. Continue by applying a coat of acrylic VELATOURA AQUA of DUROSTICK. Paint using enamel, emulsion or acrylic paints of DUROSTICK, creating a perfect, high quality finish.

2. Application

Mix well before use. VELATOURA AQUA of DUROSTICK, can be applied with a roller, a brush or an airless sprayer. Dilute by 5-10% using clean water. Once dry, sand with the appropriate sandpaper to create a smooth surface to which the final paint is applied.

■ CLEANING

Clean all tools with plenty of water, and continue with the use of a mild detergent, immediately after use.

■ COVERAGE

Approximately 10-12m²/lt per coat, depending on the texture, the absorbency of the surface and the application method.

■ STORAGE

In closed containers under normal storage conditions, for 18 months from production date.

■ SAFETY DIRECTIONS

The product needs no hazard labeling under current European and National legislation. However, it is recommended to keep away from the reach of children. If swallowed, seek immediate medical advice and show the container or label.

■ PACKAGING

Carton box with 12pcs of 750ml each one
Carton box with 4pcs of 2.5lt each one

| TECHNICAL SPECIFICATIONS | |
|---------------------------|---|
| ■ Form - Color | Thixotropic liquid - White |
| ■ Resin | Acrylic |
| ■ Density | 1.50±0.05kg/lt |
| ■ Viscosity | 1650±500 cP (spindle 3/20 rpm) |
| ■ Solids by weight | 57-65% w/w |
| ■ Solids by volume | 37-43% w/v |
| ■ pH | 8.00±0.50 |
| ■ Application temperature | From +10°C to +35°C |
| ■ Application method | Brush, roller or spray gun |
| ■ Dilution | 5-10% by volume with clean water |
| ■ Drying time | Approximately 1 hour (touch dry), depending on the ambient conditions (humidity, temperature) |
| ■ Recoating time | After 5-6 hours, depending on the ambient conditions (humidity, temperature) |

V.O.C. (Volatile Organic Compounds):

Limit value of maximum V.O.C. content per EU (Directive 2004/42/CE) for the particular product (Class A/g: 'Primers' Type WB): 30gr/lt (2010). The ready to use product contains maximum 20gr/lt V.O.C.

DUROSTICK S.A.,

MANUFACTURING OF ADHESIVES,
PAINTS & MORTARS

ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00,
Tel: +30 211 60 03 500-599, +30 210 55 16 500,
+30 210 55 98 350, Fax: +30 210 55 99 612

THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,
STREET, DA 10, GR: 570 22,
Tel: +30 2310 795 797, +30 2310 797 365,
Fax: +30 2310 797 367

Email: info@durostick.com